

Description

- Colored
- High coverage capacity
- Abrasion and shock resistant
- UV and weather resistant

Composition

Pentaphtal alkyd resins, pigments, white spirit, siccatives and fillers.

Recommended use

Intended for metallic, interior and exterior construction surfaces: concrete, cement, brick, plaster, gypsum, wood, plywood, wood particle board, fiber board.

Surface preparation

The painted surface must be clean, dry and dust, oil free.

Application

- Mix thoroughly before using.
- Use white-spirit or other benzene solvents for dilution.
- Apply the paint with brush, roller or sprayer.
- The painting should be done at the temperature no less than +5°C degrees.
- At an ambient temperature +20°C degrees, humidity – 65%, second coating should be executed approximately after 4-6 hours.
- When the work is over or suspended carefully wash the tools with solvent.
- Dispose of the metallic containers as prescribed by local legislation.

Temperature of the base when applying	from +5°C to +30°C
Paint consumption per one layer More precisely, paint consumption depends on the smoothness of the coverable surface.	0.375 l - 3-3.75 m ²
	1 l - 8-9 m ²
	3.785 l - 30-34 m ²
	20 l - 160-180 m ²
Final paint drying at an ambient temperature +20°C degree, humidity– 65%	36 hours

Sizes available

0.375 liters 3,785 liters and 20 liters metallic containers.

Storage

Keep closed, at temperature no less than + 5°C for 12 months after the manufacturing date indicated on the container.

Attention

- When working in conditions other than normal, the performances may deviate from the ones indicated above.
- The manufacturer bears no responsibility for working in violation of instructions.