

## Description

- White
- Mineral
- Environmentally clean and safe

## Composition

Gypsum, calcium carbonate, cellulose and polymer additives, retardant of set time.

## Recommended use

The putty is used for internal finishing to level non-deformable gypsum, concrete, lime, cement-lime and other surfaces in dry premises, to fill large cracks and holes.

## Surface preparation

- Prior to application, remove unsteady sections from the base, widen cracks.
- Remove dirt, dust, oil, paint, etc. from the surface.
- The unsteady sections and highly absorbing surfaces should be first treated with acrylic concentrate. It is recommended to treat the surface with "SHEN" acrylic concentrate.
- The surface should be cured for at least 4 hours, thereafter, the putty is applied.

## Making the mixture

- Pour 500 - 520 ml of water per 18 kg of dry mixture into a clean container.
- Gradually add dry mixture and stir with a mixer to obtain paste-like mass without lumps.
- Cure the mixture for 5 minutes and mix again, and then the putty is ready for use.

## Application

- Apply the mixture with a stainless metallic putty trowel on the surface.
- The works should be done at the temperature no less than +10°C degrees.
- To obtain smooth surface, polish the surface after drying of the putty.
- When the work is over or suspended, carefully wash the tools.
- Dispose of the paper bags and mixture leftovers as prescribed by local legislation.
- For fast putty drying expose to air and moderate ventilation.

Temperature of the base when applying	from +10 °C to +30°C
Amount of water per 1 kg of dry mixture	500 - 520 ml
Amount of water per 20 kg of dry mixture	10 - 10,4 l
Recommended thickness of layer	Up to 2 mm
Time of serviceability of the mixture	At least 1 hour
Shrinkage	not more than 0,6mm/m
Dry mixture consumption per 1 cm thick layer More precisely, the consumption depends on the surface quality and thickness of plaster layer.	0,815 - 0,85 kg / 1m <sup>2</sup>
	20kg / 23,5-24,5 m <sup>2</sup>

## Sizes available

Paper and polypropylene bags. Net weight 20 kg.

## Storage

Store in undamaged packaging, on palettes, in dry premises, at temperatures under 40°C and humidity under 75%, for 3months after the manufacturing date indicated on the package.

## Terms of use

- Store in a place inaccessible to children.
- When working, protect respiratory organs (chalk can cause allergy).
- Avoid contact with skin.
- In case of contact with eyes, rinse with clean water and, if needed, apply to doctor.

## Attention

- It is prohibited to add water into the mixture after its tightening: this can cause decreased mixture adhesion and cracking.
- When working in conditions other than normal, the performances may deviate from the ones indicated in the table.
- The manufacturer bears no responsibility for working in violation of instructions.